



Standard Blacks

Color Number	Carrier Resin	Tox. Status	Sugg. LDR	Pigment Loading	Suggested Applications
AC8150C	ABS	HMF	20/1	Dye System	High Gloss Jet Black often used for Cosmetic Applications
AC80999	ABS	HMF	50/1	16.5% Carbon black	Low cost Black for injecton, extrusion
RC81318	ACRYLIC	FDA	20/1	5% Channel Black	General Purpose FDA sanctioned Black
RC86044	ACRYLIC	HMF	25/1	Dye System	High Gloss Jet Black often used for Cosmetic Applications
MC8076A	EVA	HMF	50/1	50% Carbon Black	General Purpose Universal Black – Can be used for Film
MC85571 ** New Product	EVA	HMF	50/1	50% Carbon Black	Highly Loaded General Purpose Universal Black – Can be used for. PE, PP, EVA, PS*, ABS*, Nylon* New Lower cost Product
NC8218A	Nylon	HMF	25/1	10% Carbon Black	General Purpose Nylon Black
NC8765C	Nylon	HMF	33/1	Dye System	High Gloss Jet Black often used for Cosmetic Applications
LC85570 **New Product	PE	HMF	50/1 or As Required	50% Carbon Black	Highly Loaded Black for PE or PP applications. Good for Injection, Blow Molding or Heavier Gauge Film New Lower Cost Product
LC85569 **New Product	PE	HMF	50/1 or As Required	20% Carbon Black / 40% Filler	Utility Black - This product to be used only for low end injection molding applications where dispersion is not critical. Injection molding or heavy gauge film or sheet. Lowest Cost Product.
LC81319A	PE	FDA	50/1	13 % Channel Black	General Purpose FDA Approved Black. Can be used for caps, closures, rigid packaging, thermoforming.
MC82402A	PE	HMF	50/1	50% Carbon Black	Highly Loaded Black for PE or PP applications. Good for Injection or Blow Molding
TC8290B	POM	HMF	25/1	8% Carbon Black	General purpose Acetal Black

* Under Certain Conditions

Color Number	Carrier Resin	Tox. Status	Sugg. LDR	Pigment Loading	Suggested Applications
PC8399	PP	HMF	100/1	25% Carbon Black	General Purpose Polypropylene Black
PC8835	PP	FDA	25/1	4.3% Channel Black	General Purpose FDA Approved Polypropylene Black
EC86082	PET	FDA	50/1	Channel Black	JET Black FDA
EC8278A	PETG	HMF	50/1	33% Carbon Black	General Purpose Black
HC8196A	PS	HMF	50/1	30% Carbon Black	General Purpose Polystyrene
HC84158	PS	FDA	33/1	7% Channel Black	General Purpose FDA sanctioned Black
ZC8353B	Polycarbonate	HMF	25/1	6% Carbon Black	General purpose polycarbonate Black
SC8308A	SAN		25/1	8% Carbon Black	High gloss jet black
ML85808	Liquid color	HMF	.20	40% Carbon Black	Standard liquid color

* Under Certain Conditions